




# Technical Data Sheet



Certificate No: 0338-CPR-0643









## TG 3030S


**CERTIFICATION  
SERVICES**

Notified Body

**TG 3030S** is a polypropylene extruded biaxial geogrid manufactured at one of THRACE NWs & GEOs S.A. facilities that have achieved **ISO 9001:2008** certification for its systematic approach to quality. The construction of the biaxial geogrid makes it ideal for the following applications with its main function being "Reinforcement".

### Applications and intended uses of the extruded Biaxial Geogrid

							
EN 13249	EN 13250	EN 13251	EN 13253	EN 13254	EN 13255	EN 13257	EN 13265
R	R	R	R	R	R	R	R



R=Reinforcement

It is resistant to commonly encountered soil chemicals, mildew and insects and is non-biodegradable. **TG 3030S** conforms to the property values listed below. Technical data are based on statistical analysis on 95% confidence limit.

PROPERTY	TEST METHOD	VALUE	METRIC UNITS	TOLERANCE
<b>MECHANICAL</b>				
Tensile Strength (MD/CD)	EN ISO 10319	Average	kN/m	30/30
Elongation at Maximum Load (MD/CD)	EN ISO 10319	Average	%	12/9
Tensile Strength at 2% Strain (MD/CD)	EN ISO 10319	Average	kN/m	10/10
Tensile Strength at 5% Strain (MD/CD)	EN ISO 10319	Average	kN/m	21/23
Rib Strength (MD/CD)	GRI GG1	Average	kN/m	29/29
Junction Strength (MD/CD)	GRI GG2	Average	kN/m	27/27
Multi-axial secant stiffness at 0.5% strain ( $J_{0.5\%}$ )	DIN 61551	Average	kN/m	900
Overall Flexural Rigidity-Stiffness <sup>5</sup>	ASTM D 1388, mod. Via ASTM D 7748	Average	mg-cm	400000
<b>ENDURANCE</b>				
Weathering Resistance (MD/CD)	EN 12224	Average	%retain strength	100/100
Resistance to Liquids – Acid (MD/CD)	EN 14030	Average	%retain strength	100/100
Resistance to Liquids – Alkaline (MD/CD)	EN 14030	Average	%retain strength	100/100
Resistance to oxidation (28days @ 110 °C) (MD/CD)	EN ISO 13438	Average	%retain strength	100/100
Resistance to oxidation (140days @ 110 °C) (MD/CD)	EN ISO 13438	Average	%retain strength	100/100
Resistance to Soil Burial (MD/CD)	EN 12225	Average	%retain strength	100/100
<b>PHYSICAL</b>				
Grid Opening Size (MD/CD)	Measured	Average	mm	40/40
Carbon Black	ASTM D1603	Average	%	2
<b>STANDARD PACKAGING</b>				
Roll Width	Measured	Typical	m	3.95
Roll Length	Measured	Typical	m	50

#### NOTES:

- THRACE NWs&GEOs S.A. reserves the right to alter product specifications at any time without prior notice. It is the responsibility of all users to satisfy themselves that the above data are current.
- The geogrids listed are CE marked and they come along with a CE certificate after a customer request.
- Polypropylene is the constituent polymer used in the production of the TG geogrid series.
- To be covered within one month after installation. Predicted to be durable for more than 120 years in soil temperatures > 25°C and is resistant to highly acid and alkaline environments on the basis of a durability assessment.
- Sample usually delivered to client in rolled condition, residual curl memory of material may have bias test results.

The information contained herein is furnished without charge or obligation and the recipient assumes all the responsibility for its use. Because conditions for use and handling may vary and are beyond our control, THRACE NWs&GEOs S.A. makes no representation about, and is not responsible or liable for, the accuracy or reliability of said information or performance of any product. Any specification, properties or applications listed herein are provided as information only in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as any recommendation to infringe any patent.

**TÜV TUV**  
AUSTRIA AUSTRIA  
HELLAS HELLAS  
EN ISO 14001:2004 EN ISO 9001:2008  
Reg. No: 04013108 Reg. No: 01010018