



Composite Reinforcement Solution

CompoGrid 100L Pavement Reinforcement System is manufactured at a Saint-Gobain ADFORS facility that has achieved ISO 9001:2008 certification, registration PRA0003834 and meets the requirements of EN15381. CompoGrid is a composite material consisting of fiberglass reinforcement grid coated in a patented elastomeric polymer, bonded to a spun bond polyester textile. GlasGrid CG100L conforms to the property values listed below, which have been derived from quality conformance testing performed by an accredited laboratory:

Property	Metric	Imperial	Test Method
Tensile Strength (MD x XD) (Ultimate)	115 x 115 - 15 kN/m	657 x 657 - 86 lbs/in	EN-ISO 10319:2008
Tensile Elongation (Ultimate)	2,5 ± 0,5 %	2.5 ± 0.5%	EN-ISO 10319:2008
Tensile Resistance @ 2% Strain	95 x 95 ± 20 kN/m	542 x 542 ± 114 lbs/in	EN-ISO 10319:2008
Secant Stiffness EA @ 1% Strain (MD x XD)	4.600 x 4.600 ± 600 N/mm	26,267 x 26,267 ± 3,426 lbs/in	EN-ISO 10319:2008
Young's Modulus E	73.000 MPa	10.6 x 10 ⁶ psi	
Mass per Unit Area	439 g/m ²	13 oz/yd ²	ISO 9864
Asphalt Retention	0,35 ± 0,15 l/m ²	0.08 ± 0,03 gal/yd ²	ASTM D6140 EN 15381 Annex C
Melting Point Coating Melting Point Glass	>232° C >820° C	>450° F >1508° F	ASTM D276/EN-ISO 3146 ASTM C338
Roll Length	100 m	328 ft	
Roll Width	1,0; 1,5; 2,0; 3,0 m	3.3, 5, 6.6, 9.9 ft	
Roll Area	100, 150, 200, 300 m ²	120, 179, 239, 359 yd ²	
Grid Size (Center to Center of Strand)	25 x 25 mm	1.0 x 1.0 in	
Material	Fiberglass reinforcement with modified polymer coating and bonded to a spun bond polyester textile specifically engineered for asphalt overlays		

The values and tolerances given are obtained in our laboratories and in accredited testing institutions. All imperial values are approximate. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.



1021-CPR-040/15
2015



Saint-Gobain ADFORS
www.adfors.com
Email: glasgrid.eu@saint-gobain.com